



















# FIRE RETARDANT POPULAR PLYWOOD “IGNIPASComp”



**INVERNIZZI**  
Plywood Tradition

This technical datasheet is not a contract reference document. Given average values are linked to internal test carried out in our internal laboratories (unless specified differently) and may be subject to changes without any previous advice in accordance to production requirements.

APPLICATIONS	 FURNITURE	 CONSTRUCTION	 HOSPITALS & CLINICS	 MOTORHOMES & CARAVANS	 SHIPBUILDING	 RAILWAYS			
PHYSICAL/MECHANICAL PROPERTIES	REFERENCE STANDARD	MEASURING UNIT	THICKNESS (mm)						
			10	12	15	18, 20	25	30	38, 40
 MINIMUM NUMBER OF LAYERS			5	7	7	9	11	13	17
 DENSITY	EN 323	Kg/m <sup>3</sup>	420 - 460						
 BENDING STRENGTH (IN LENGTH DIRECTION)	EN 310	N/mm <sup>2</sup>	> 12 (min. detected value)						
 BENDING STRENGTH (IN WIDTH DIRECTION)	EN 310	N/mm <sup>2</sup>	> 20 (min. detected value)						
 MODULUS OF ELASTICITY IN BENDING (IN LENGTH DIRECTION)	EN 310	N/mm <sup>2</sup>	> 2000 (min. detected value)						
 MODULUS OF ELASTICITY IN BENDING (IN WIDTH DIRECTION)	EN 310	N/mm <sup>2</sup>	> 2000 (min. detected value)						
 MOISTURE CONTENT	EN 322	%	10±2						
 AVERAGE FORMALDEHYDE RELEASE	EN 717/2	mgHCHO/m <sup>2</sup> h	<3,5 (Class E1 - standard)						
	ASTM E 1333	ppm	<0,05 CARB phase 2 (available on request)						
	EN 16516	ppm	<0,1 UBA - BAnz AT 26.11.2018 B2 (on request)						
 BONDING REQUIREMENT DETERMINATION	EN 314-1	Class 1: bonding is made using urea-formaldehyde resins (UF) and meets the requirements provided by the Class 1 bonding type -Panels to be used in dry environments (EN 636 – Plywood – Specifications).							
	EN 314-2	Class 2: bonding is made using melamine-urea-formaldehyde resins (MUF) and meets the requirements provided by the Class 2 bonding type -Panels to be used in covered (roofed) exteriors (EN 636 – Plywood – Specifications).							
 REACTION TO FIRE CLASS	EN 13501-1	B - s2, d0 CE fire rated panels							
 LAYERS' COMPOSITION	EN 313-2	All outer faces and inner layers are composed exclusively of poplar wood veneers, fire-treated individually and then pressed together. Upon request, panels made with veneers coming from a sustainable forest management (FSC® / PEFC) are available.							
 ENGINEERING TOLERANCES	EN 315	Length & Width: ± 3,5 mm Thicknesses ≥ 10 mm up to ≤ 25 mm: + 0,2 mm - 0,4 mm Thicknesses > 25 mm up to ≤ 40 mm: + 0,0 mm - 0,4 mm							
☆☆☆ CLASSIFICATION BY SURFACE APPEARANCE	EN 635-2	Italian poplar faces/backs or, as alternative: II, III (B or BB)							
CE MARKING	EN 13986	All Plywood panels are CE marked for internal use as non-structural components							
	EN 13986	CE 2+ marking (on request) for internal use as structural components (applies to panels with > 9 mm thickness and > 400 Kg/m <sup>3</sup> density)							

INVERNIZZI S.p.A. Strada Provinciale per Gussola, 26030 Solarolo Rainerio (CR) ITALY - Tel. +39 0375 31331 - Fax +39 0375 3133222/3 - Cap.Soc. 2.250.000 i.v. - Reg. Imp. di Cremona N. 3113 R.E.A. di Cremona N. 93343 - P.IVA e C.F. 00189240195 - N. Iden. CEE IT 00189240195 - [www.invernizzi-spa.com](http://www.invernizzi-spa.com) - [info@invernizzi-spa.com](mailto:info@invernizzi-spa.com)

